



EGYPTIAN PETROCHEMICALS CO.

PVC RESIN K- VALUE 67 SPECIFICATIONS

		SPECIFICATION
I.V		0.90-0.94
POROSITY	ml/gm	0.20-0.32
A.B.D	gm/ml	0.49-0.56
PARTICAL SIZE	RET40 %max	1
	RET60 %max	5
	TH.140 %max	25
A.P.S	MICRON	150-170
H.L	%max	0.3
D.R	/100 INCH² MAX.	6
F.E	/36 INCH² MAX.	20
F.T	SEC.	15-25
R.VCM	PPM max.	1

*The data in this leaflet are given to the best of our knowledge . The suitability of the products or material has to be determined by the user & all safety precautions have to be taken by himself. We make no warranty or guarantee as to the results using these products since the use of these products is not under EPC control .



EGYPTIAN PETROCHEMICALS CO.
Km 36 Alex/Cairo Desert Road Amreyia, Alex - Egypt
FAX: 00203 4770029 TEL: 00203 4770012 - 19
E-mail: epc@egy-petrochem.com
Web site: www.egy-petrochem.com

